

# Vacfilm® 400Y

## Vacuum bagging film

Ideally suited to aerospace and wind energy applications

### Features

- Tough, high elongation elastomeric film, suitable for de-bulking applications and oven curing of composites up to temperatures of 150°C (302°F).
- Due to the film's high elasticity, the necessity for pleats is reduced in debulk operations.
- Premium film for wind energy applications.
- Excellent recovery after elongation enables the film to be reused on subsequent debulk operations, making this film one of the most cost effective debulk products in our range.
- Good release from sealant tape.

### Properties

Maximum use temperature	150°C (302°F)		
Colour	Yellow		
Tensile strength at break (ASTM D882)	Transverse direction	40MPa	5802PSI
	Machine direction	37MPa	5366PSI
Elongation at break (ASTM D882)	Transverse direction	370%	
	Machine direction	360%	
Yield	50µm (0.002in)	19.12m <sup>2</sup> /kg	10.37yd <sup>2</sup> /lb
	65µm (0.0025in)	14.71m <sup>2</sup> /kg	7.98yd <sup>2</sup> /lb
	75µm (0.003in)	12.74m <sup>2</sup> /kg	6.91yd <sup>2</sup> /lb

### Availability

Thickness	50, 65 and 75µm	0.002, 0.0025 and 0.003in
Roll weight	Up to 45kg	Up to 100lbs
Widths	Up to 10.05m (open)	Up to 394in (open)
Formats available	Tube, sheet, V sheet, gusseted and C-fold	

### Storage

Vacfilm 400Y is a hydrophilic material. Moisture and water act as plasticisers. The level of moisture content at time of use is therefore an important factor for successful performance. The higher the moisture content the more flexible they become. Conversely at lower moisture levels flexibility is limited.

Do not store rolls vertically on their ends.

### Health & safety

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.

© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.