

B100

Peel ply

Ideally suited to a wide range of composite processing applications

Features

- Lightweight, porous nylon peel ply.
- Heat set and scoured, for use directly against laminates or bond lines, particularly where secondary bonding, painting or finishing is required.
- Imparts a fine weave pattern upon removal from the laminate.
- Strips cleanly and quickly from most commercial resin systems.
- Available coated and non-coated depending on user requirement.
- Recommended for composite manufacture and metal bonding applications.
- CYTEC does not recommend the use of woven nylon fabrics with phenolic resin or pre-preg systems as acid in the catalyst can break down nylon materials. Therefore, we recommend that customers conduct their own internal compatibility tests.

Properties

Maximum use temperature	204°C	400°F
Colour	White	
Fabric type	Nylon	
Fabric weight	58g/m ²	1.70oz/yd ²

Availability

Standard width	1.47m	58in
Standard length	100m	109yd
Slit widths available		

Storage

No special storage conditions required.

Health & safety

Handling of these products must conform to individual company guidelines and health and safety regulations.

All statements, technical information and recommendations contained in this data sheet are given in good faith and are based on tests believed to be reliable, but their accuracy and completeness are not guaranteed. They do not constitute an offer to any person and shall not be deemed to form the basis of any subsequent contract. All products are sold subject to the Cytec's Standard Terms and conditions of Sale. Accordingly, the user shall determine the suitability of the products for their intended use prior to purchase and shall assume all risk and liability in connection therewith. It is the responsibility of those wishing to sell items made from or embodying the products to inform the user of the properties of the products and the purposes for which they may be suitable, together with all precautionary measures required in handling those products. The information contained herein is under constant review and liable to be modified from time to time.

© Copyright 2012 – Cytec Process Materials (Keighley) Ltd, Cytec Process Materials (CA) Inc, Cytec Process Materials (Toulouse) Sarl, Cytec Process Materials (Milan) Srl. All rights reserved worldwide. All trademarks or registered trademarks are the property of their respective owners.